1/2





 $240 \ \square \ \square\square\square \ \square\square\square \ \square\square\square\square\square\square\square\square\square\square\square\square3000\square\square\square\square$





Test Report

Report No.: AGC02096180101-002

Date:Jan.29, 2018

Page 1 of 2

Applicant:

Shenzhen Chenyangguang Garment Accessory Co., Ltd.

Address:

1302, Xuyuan Building, Longgang Road, Longgang Distric, Shenzhen City, Guangdong

Province,China

Report on the submitted sample(s) said to be:

Sample Name

: Velvet elastic band/Imeter

Model No.

: #194

Ingredient

: 100% Nylon

Color

Deep Navy : Panpacific

Buyer Country of origin

: China

Country of destination

: EU,USA

Sample Received Date : Jan.24, 2018

Testing Period

; Jan.24, 2018 to Jan.29, 2018

Test Requested

As specified by client, to determine the color fastness to rubbing of the submitted

Test Method

: Please refer to next page(s).

Test Result

: Please refer to next page(s).

Tested by, Charry gin

Qiuxiaoting, Cherry. Qiu

Reviewed by: Grace r Ruanxuejie, Grace ruan

Test Engineer

Laboratory Supervisor



No.17 C 047243

Tel: +86-755 8358 3833 Fax: +86-755 2531 6612 E-mail: agc01@agc-cert.com @ 400 089 2118 Add: Bustong 2, No.171, Maihus Road, Shangmellin, Fatlan District, Shanghen, Guangdong China



Test Report

Report No.: AGC02096180101-002

Date:Jan.29, 2018

Page 2 of 2

Test Result(s):

1. Test Results of Color fastness to rubbing

Item	Test method	Result		
		1	1	
Color fastness to rubbing (Grade)	ISO 105-X12-2016	dry	4-5	٦
		wet	4-5	

Color fastness grade: grey scale (5 grade is good, 1 grade is bad).

Sample Description

1 Blue cloth

The photo of the sample



No.17 C 047244

Tel: +86-755 8358 3633 Fax: +86-755 2931 6612 E-mail: appl (glaps-cent com _g. 400 689 2118 Add: Bwilding 2. No. 171, Methua Road, Shangmailin, Futian Diatriot, Shangher, Guangdong China